


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B44F	A2	(11) International Publication Number: WO 00/46045 (43) International Publication Date: 10 August 2000 (10.08.00)
<p>(21) International Application Number: PCT/US00/02863</p> <p>(22) International Filing Date: 3 February 2000 (03.02.00)</p> <p>(30) Priority Data: 60/118,620 4 February 1999 (04.02.99) US</p> <p>(71) Applicant (for all designated States except US): TEXTRON AUTOMOTIVE COMPANY INC. [US/US]; 750 Stephenson Highway, Troy, MI 48083 (US).</p> <p>(72) Inventor; and (75) Inventor/Applicant (for US only): GRAY, John, D. [US/US]; 17 Bridge Street, Union, NH 03887 (US).</p> <p>(74) Agent: JONES, Eric, T.; Reising, Ethington, Barnes, Kisselle, Learman & McCulloch, P.C., P.O. Box 4390, Troy, MI 48099-4390 (US).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published Without international search report and to be republished upon receipt of that report.</p>

(54) Title: METHOD FOR FORMING DESIGN IN A LAYERED PANEL USING A LASER

(57) Abstract

A method for forming a design (14) in a panel (12) includes providing an outer panel layer (16) on an inner panel layer (18) to form a single composite panel (12) including two layers (16, 18). The design (14) is then formed into the panel (12) by forming voids (17) in the outer layer (16). The voids (17) are formed by exposing predetermined regions of the outer layer (16) to a laser beam (32) that burns, vaporizes or otherwise removes portions of the outer layer (16) in each exposed region. The voids (17) create the design (14) by exposing the inner panel (12) layer.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

METHOD FOR FORMING DESIGN IN A LAYERED PANEL USING A LASER

This application claims priority of U.S. provisional patent application
5 Serial No. 60/118,620 filed February 4, 1999.

TECHNICAL FIELD OF THE INVENTION

This invention relates generally to a method for forming a multi-colored or
10 two-toned decorative outer class A surface or first surface on a skin or panel.

INVENTION BACKGROUND

Currently, multi-colored or two-tone decorative surfaces are produced on
15 skins or panels by a number of different processes. In general, these processes can be categorized as either coating methods such as painting; or infusion methods such as material pigmentation, i.e., mixing color into plastics materials before the materials are formed into skins or panels.

Processes that employ infusion include slush mold processes where pre-pigmented dry particulate plastic materials are cast against a heated slush mold surface. The cast materials melt on the heated surface to form a shell or skin. Various methods for producing multi-colored or two-tone decorative surfaces includes the use of one or more gaskets in the slush molding process. According to
20 one method, one or more gaskets are used to form a decorative surface on a plastic skin or panel comprising at least two distinct separate areas of plastic material. The gasket is pressed against a heated slush mold surface to separate castings of different-colored charges of dry, particulate plastics material.

Another method for producing multi-colored or two-tone decorative
30 surfaces on skins or panels using pre-pigmented plastic materials includes the masking of certain areas on a heatable slush mold surface. According to this

method, a first or "outer" layer is formed by casting a first plastics material against a portion of the heated mold surface. The masking is then removed and a second or "inner" layer is formed by casting a second plastic material of a different color or shade against the outer layer and also onto the exposed areas of the heated mold surface that had been masked during the first casting step.

Each of the above slush mold methods produces a plastic skin or panel having a composite two-tone outer surface. Because the two plastic materials forming the composite surface are cast against the same heated mold surface they form respective outer surfaces that lie flush in relation to each other. In other words, the composite surface is a single-level, smooth surface.

It is also known, in certain automotive applications, for skins, such as seat upholstery, to include textured surfaces comprising a plurality of small diameter cylindrical depressions or through-holes. The depressions or holes formed in these skins are on the order of one millimeter in diameter and are closely spaced in a regular pattern across an entire outer exposed surfaces of such skins.

What is needed is a quick and accurate method for mass producing skins or panels having multi-colored or two-tone designs on an outer surface of each skin or panel.

SUMMARY OF THE INVENTION

According to the invention, a method is provided for forming a design in a panel (12). The method includes providing an outer layer (16), an inner layer (18) and providing the outer layer (16) on the inner layer (18) in a layered disposition. The method further includes providing a design (14) in the panel (12) by forming voids (17) in the outer layer (16) that expose the inner layer (18).

30

The voids (17) are provided in the outer layer (16) by exposing predetermined regions of the outer layer (16) to a laser beam (32) capable of

burning, evaporating or otherwise removing portions of the outer layer (16) in each exposed region. The employment of laser technology allows detailed designs to be created in the outer class A surfaces of large numbers of like panels both quickly and accurately in an assembly line process.

5

BRIEF DRAWING DESCRIPTION

To better understand and appreciate the invention, refer to the following detailed description in connection with the accompanying drawings:

10 Figure 1 is a perspective view of a plastic panel having a design formed according to the inventive method;

 Figure 2 is a partial cross-sectional edge view of the plastic skin of Figure 1 before design formation;

15 Figure 3 is a partial cross-sectional edge view of the plastic skin of Figure 1;

 Figure 4 is a schematic front view of the panel of Figure 1 supported on a holding fixture and being lased by a laser beam from a laser gun, a laser controller and a laser drive mechanism constructed according to the invention, an alternate holding fixture drive mechanism being shown in phantom;

20 Figure 5 is a partial cross-sectional edge view of the plastic skin of Figure 1 with outer and inner layers bonded together by an adhesive; and

 Figure 6 is a perspective view of a panel having a tear seam formed according to the inventive method to aid in the deployment of an air bag from behind the panel.

25

PREFERRED EMBODIMENT DESCRIPTION

 A two-tone design formed on and into an outer surface 10 of a plastic skin or panel 12 according to the inventive method is generally indicated at 14 in
30 Figures 1 and 3. According to the method, the skin or panel 12 is first manufactured without a design as shown in Figure 2. The skin or panel 12 is manufactured to include at least two layers as shown at 16 and 18 in Figures 1-3.

The two layers may completely overlap through the skin or panel, or may partially overlap in an area where the design is to be applied according to the invention. The two layers 16, 18 comprise respective first and second materials of different appearance, preferably plastic materials. The difference in appearance between the
5 respective first and second plastic materials may be due to differences in any one of a number of different visually discernable attributes including but not limited to color, intensity, texture, pattern, gloss, and thickness.

As used herein, a difference in appearance may be visually discernable
10 via ordinary viewing with the naked eye or where more objectivity is desired, discernable via a difference in numeric values as measured by any industry accepted appearance measurement test. For color, difference is preferably measured as the difference in any individual numerical reading obtained from a spectrophotometer using the CIE 1976 L* a* b* scales. For texture, which
15 includes attributes such as grain, orange peel, and surface roughness, a profilometer is preferred to obtain numerical differences. For gloss, a gloss meter is preferred to measure differences in degree of reflective light.

The skin component may be formed from one or more plastics materials
20 including but not limited to polyvinyl chlorides (PVC), thermoplastic urethanes (TPU), thermoplastic olefins (TPO), thermoset urethanes, polyesters, rubbers, polypropylenes, and polyethylenes. The layers 16, 18 may be formed by any known method including but not limited to casting, vacuum forming, blow molding, injection molding, rotational molding, and spray coating. The layers 16,
25 18 may each be formed separately and then bonded together, or may be manufactured as a single composition including two or more layers 16, 18. In the embodiment of Figures 1-3 the outer layer 16 is of a light colored plastics material and has a thickness of approximately .010", but may be as little as .001" as in the case of a spray coating. The second or underlying layer 18 shown in Figures 1-3 is
30 of a darker colored plastics material and has a thickness of approximately .040". As shown in Figures 1 and 3, the areas where portions of the first or outer layer 16 have been removed leave exposed the underlying, darker second layer 18. While

plastic materials are preferred, other materials which could be substituted in any combination and in any relative position including but not limited to textiles, leather, metals, wood, and natural and synthetic resins.

5 After formation, the skin or panel 12 is transported from a manufacturing area to a laser station shown schematically in FIG. 4. At the laser station the skin or panel 12 is placed on a holding fixture 30 and the outer surface 10 of a first 16 or "outer" one of the two layers 16, 18 is exposed to a laser beam 32 produced by a laser beam generator 34 of a laser gun 36 and delivered by a beam delivery
10 mechanism 38 of the gun 36. The laser gun 36 may be connected to an electronic controller 40 programmed to provide and remove the laser beam 32 by either energizing and deenergizing the beam generator 34 or by directing and redirecting or blocking and unblocking the laser beam 32 generated by the beam generator 34. The controller 40 may also be programmed to command a laser gun drive
15 mechanism 42 to move the laser beam 32 to various predetermined points on the panel 12 or to direct the laser beam 32 toward some point away from the panel. The electronic controller 40 may be programmed to move the laser beam 32 in accordance with a predetermined program to a predetermined series of positions adjacent portions of the outer surface 10 of the first or outer layer 16 of the skin or
20 panel 12 that are to be removed to expose corresponding portions of a second 18 or underlying one of the two layers 16, 18 in a predetermined pattern to form a desired pattern. In each position of the predetermined series of positions the controller 40 then commands the laser gun 36 to operate in such a way as to cause an emitted laser beam 32 to burn away, evaporate or otherwise remove portions of the first
25 layer 16 of the panel 12 to leave corresponding voids 17 that expose corresponding portions of the second layer 18 beneath. As shown in Figures 1 and 3, the laser beam 32 may also be caused to burn a short distance into the second layer 18 to insure that the second material is exposed despite any variations in thickness in the first layer 16.

30

As shown in phantom in FIG. 4, a holding fixture drive 44 may be operatively connected to the holding fixture 30 and/or the panel 12 in place of the

laser gun drive 42. In such embodiments the controller 40 is connected to the fixture drive 44 and programmed to move the panel 12 in accordance with a predetermined program to a predetermined series of positions holding portions of the outer surface 10 in the path of the laser beam 32 to form the desired pattern.

5

The removed portions and resulting voids 17 may be of any configuration, size and number to create a desired decorative effect. The configuration of the voids 17 may include holes of various shapes, as shown at 20 in Figures 1 and 3; lines as shown at 22, Figure 1; and/or logos, or logo enhancements as shown at 24 in Figure 1. In addition, a number of voids 17 may be arranged to form a composite logo image or other design 14. The various configurations of voids 17 could, for example, be formed on automotive seat covers or interior trim panels. In other embodiments the voids 17 may be configured to provide decoration and/or first surface weakening of a supplemental inflatable restraint (SIR) door opening.

10
15

The skin or panel described above is preferably of a type used for a vehicle trim panel. However, other uses include, but are not limited to toys, construction, furniture, luggage, or any other application where such an aesthetic appearance or function is desirable.

20

As set forth in the claims, the method includes providing an outer panel layer 16 comprising a first plastic material and an inner panel layer 18 comprising a second plastic material that is different in appearance than the first material. The difference in appearance between the first and second materials may be due to differences in any one of a number of different visually discernable attributes such as color, intensity, texture pattern, gloss, and thickness. The inner and outer panel layer 16s may be the inner and outer panels 12 of an automotive seat cover or of an interior automotive trim panel 12.

25

30

As shown in FIG. 5, in providing the outer layer 16 on the inner layer 18 in a layered disposition, an adhesive 50 may first be provided between the outer

and inner layers 18. Alternatively, the outer and inner layers 18 may be formed by casting the first and second materials, in powder or particulate form, against a heated mold surface in a slush molding process.

5 A design 14 is provided in the panel 12 by forming voids 17 in the outer layer 16 such that that the inner layer 18 is exposed and visible through the voids 17. The voids 17 may be formed to create a desired decorative effect by, for example, configuring the voids 17 to include holes of various shapes such as linear shapes 22, logos or logo enhancements 24, composite logo images and/or
10 designs 14 formed by providing a number of voids 17 adjacent one another in a predetermined pattern. As shown in FIG. 6, other embodiments may include a weakened region as shown at 46 comprising a plurality of voids 17' provided in a pattern 46 or a weakened region as shown at 48 comprising a single elongated void 17'. Each of these weakened regions 46, 48 are formed in an outer layer 16'
15 of a multi-layer panel 12' and define a supplemental inflatable restraint door opening.

 The voids 17 are provided by exposing predetermined regions of the outer layer 16 to a laser beam 32 capable of burning, evaporating or otherwise
20 removing portions of the outer layer 16 in each exposed region. A desired remaining thickness of the second material may be provided beneath each void by causing the laser to burn through the outer layer 16 and, controllably, a desired fixed depth into the inner layer 18.

25 The laser beam 32 is directed by connecting a controller 40 to a drive mechanism 42 that is operatively connected to either the panel 12 or a laser beam delivery mechanism 38. The controller 40 is programmed to create a predetermined design 14 by commanding the drive mechanism 42 to move one of the panel 12 and the laser beam 32 in a predetermined pattern relative to one
30 another. The controller 40 is also programmed to turn off or redirect the laser when the laser beam 32 has cut to a predetermined depth in to the panel 12.

I intend this description to illustrate certain embodiments of the invention rather than to limit the invention. Therefore I have used descriptive words rather than limiting words.

5. Obviously, it's possible to modify this invention from what the description teaches. One may practice the invention other than as described.

What is claimed is:

1. A method for forming a design in a panel (12); the method including the steps of:

- 5 providing a panel outer layer (16);
 providing a panel inner layer (18);
 providing the outer layer (16) on the inner layer (18) in a layered disposition;
 providing a design (14) by forming voids (17) in the outer layer (16), the
10 voids (17) exposing the inner layer (18); and
 providing the voids (17) by exposing predetermined regions of the outer layer (16) to a laser beam (32) capable of burning, evaporating or otherwise removing portions of the outer layer (16) in each exposed region.

- 15 2. The method of claim 1 in which:
 the step of providing an outer layer (16) includes providing a layer comprising a first material; and
 the step of providing the inner layer (18) includes providing a layer that comprises a second material different in appearance from the first material.

- 20 3. The method of claim 1 in which:
 the step of providing an outer layer (16) includes providing an outer skin (16) for an automotive seat cover (12); and
 the step of providing an inner layer (18) includes providing an inner layer
25 (18) of an automotive seat cover (12).

4. The method of claim 1 in which:
 the step of providing an outer layer (16) includes providing an outer skin (16) for an automotive interior trim panel (12); and
30 the step of providing an inner layer (18) includes providing an inner layer (18) of an automotive interior trim panel (12).

5. The method of claim 1 including the additional step of providing an adhesive (50) between the outer and inner layers (16, 18) before the step of providing the outer layer (16) on the inner layer (18).

5. 6. The method of claim 1 in which the step of providing the outer layer (16) on the inner layer (18) and the steps of providing the outer and inner layers (16, 18) include casting the first and second materials against a heated mold surface.

10 7. The method of claim 1 in which the step of providing a design (14) includes forming the voids (17) in a predetermined pattern to create a desired decorative effect.

8. The method of claim 1 in which the step of providing a design (14)
15 includes configuring the voids (17) to include holes (20) of various shapes.

9. The method of claim 1 in which the step of providing a design (14) includes providing the voids (17) in a pattern forming a weakened region (46, 48) in the outer layer (16) defining a supplemental inflatable restraint door opening.

20 10. The method of claim 1 in which the step of providing the voids (17) includes providing a desired remaining thickness of the second material beneath each void (17) by causing the laser beam (32) to burn through the outer layer (16) and a desired depth into the inner layer (18).

25 11. The method of claim 1 in which the step of providing the voids (17) includes directing the laser beam (32) by connecting a controller to a drive mechanism that is operatively connected to one of the panel (12) and a laser beam delivery mechanism (38) of a laser gun (36), the controller being programmed to
30 create a predetermined design (14) by commanding the drive mechanism to move one of the panel (12) and the laser beam (32) in a predetermined pattern relative to one another.

- 11 -

12. The method of claim 11 in which the step of providing the voids (17) includes connecting a controller (40) to the laser gun (36), the controller (40) being programmed to turn off or redirect the laser beam (32) once the laser beam (32) has cut to a predetermined depth into the panel (12).

5 .




Fig 2








FIG 3







(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 August 2000 (10.08.2000)

PCT

(10) International Publication Number
WO 00/46045 A3

- (51) International Patent Classification⁷: **B44C 1/22**, 3/00, B60R 13/02, B60N 2/58
- (21) International Application Number: **PCT/US00/02863**
- (22) International Filing Date: 3 February 2000 (03.02.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/118,620 4 February 1999 (04.02.1999) **US**
- (71) Applicant (for all designated States except US): **TEX-TRON AUTOMOTIVE COMPANY INC. [US/US]; 750 Stephenson Highway, Troy, MI 48083 (US).**
- (74) Agent: **JONES, Eric, T.; Reising, Ethington, Barnes, Kisselle, Learman & McCulloch, P.C., P.O. Box 4390, Troy, MI 48099-4390 (US).**
- (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).


Published:

— With international search report.

- (72) Inventor: **and**
- (75) Inventor/Applicant (for US only): **GRAY, John, D. [US/US], 17 Bridge Street, Union, NH 03887 (US).**
- (88) Date of publication of the international search report:
28 December 2000

[Continued on next page]

(54) Title: **METHOD FOR FORMING DESIGN IN A LAYERED PANEL USING A LASER**



(57) Abstract: A method for forming a design (14) in a panel (12) includes providing an outer panel layer (16) on an inner panel layer (18) to form a single composite panel (12) including two layers (16, 18). The design (14) is then formed into the panel (12) by forming voids (17) in the outer layer (16). The voids (17) are formed by exposing predetermined regions of the outer layer (16) to a laser beam (32) that burns, vaporizes or otherwise removes portions of the outer layer (16) in each exposed region. The voids (17) create the design (14) by exposing the inner panel (12) layer.

WO 00/46045 A3



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/02863

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B44C1/22 B44C3/00 B60R13/02 B60N2/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B44C B60R B60N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 44 19 197 A (VOLKSWAGENWERK AG) 15 December 1994 (1994-12-15) column 1, line 58 -column 2, line 5 ---	1,2
X	PATENT ABSTRACTS OF JAPAN vol. 012, no. 485 (M-777), 19 December 1988 (1988-12-19) & JP 63 205291 A (NKK CORP), 24 August 1988 (1988-08-24) abstract ---	1,2
X	FR 2 575 114 A (CALVADOS HUBERT) 27 June 1986 (1986-06-27) page 1, line 28 -page 2, line 19 page 3, line 1 - line 12 -----	1,2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

7 June 2000

Date of mailing of the international search report

08. 09. 2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Herrmann, J

INTERNATIONAL SEARCH REPORT

In international application No.
PCT/US 00/02863

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

The international Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1(partially) and 2

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

1. Claim : 1 (partially) and 2
claim 1 (partially) and and claim 2
2. Claim : 1 (partially) and 3
1 (partially) and claim 3
3. Claim : 1 (partially) and 4
1 (partially) and claim 4
4. Claim : 1 (partially) and 5
1 (partially) and claim 5
5. Claim : 1 (partially) and 6
1 (partially) and claim 6
6. Claim : 1 (partially) and 7
1 (partially) and claim 7
7. Claim : 1 (partially) and 8
1 (partially) and claim 8
8. Claim : 1 (partially) and 9
1 (partially) and claim 9
9. Claim : 10
1 (partially) and claim 10
10. Claims: 1 (partially), 11 and 12
1 (partially) and claim 11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/02863

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 4419197 A	15-12-1994	NONE	
JP 63205291 A	24-08-1988	NONE	
FR 2575114 A	27-06-1986	NONE	

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 August 2000 (10.08.2000)


PCT

(10) International Publication Number
WO 00/46045 A3

- (51) International Patent Classification⁷: B44C 1/22, 3/00, B60R 13/02, B60N 2/58
- (21) International Application Number: PCT/US00/02863
- (22) International Filing Date: 3 February 2000 (03.02.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/118,620 4 February 1999 (04.02.1999) US
- (71) Applicant (for all designated States except US): **TEX-TRON AUTOMOTIVE COMPANY INC.** [US/US]; 750 Stephenson Highway, Troy, MI 48083 (US).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): **GRAY, John, D.** [US/US]; 17 Bridge Street, Union, NH 03887 (US).
- (74) Agent: **JONES, Eric, T.**; Reising, Ethington, Barnes, Kisselle, Learman & McCulloch, P.C., P.O. Box 4390, Troy, MI 48099-4390 (US).
- (81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published: — with international search report

[Continued on next page]

(54) Title: METHOD FOR FORMING DESIGN IN A LAYERED PANEL USING A LASER



(57) Abstract: A method for forming a design (14) in a panel (12) includes providing an outer panel layer (16) on an inner panel layer (18) to form a single composite panel (12) including two layers (16, 18). The design (14) is then formed into the panel (12) by forming voids (17) in the outer layer (16). The voids (17) are formed by exposing predetermined regions of the outer layer (16) to a laser beam (32) that burns, vaporizes or otherwise removes portions of the outer layer (16) in each exposed region. The voids (17) create the design (14) by exposing the inner panel (12) layer.

WO 00/46045 A3



- (88) Date of publication of the international search report:
28 December 2000
- (48) Date of publication of this corrected version:
25 October 2001

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

- (15) Information about Correction:
see PCT Gazette No. 43/2001 of 25 October 2001, Section
II

METHOD FOR FORMING DESIGN IN A LAYERED PANEL USING A LASER

5 This application claims priority of U.S. provisional patent application
Serial No. 60/118,620 filed February 4, 1999.

TECHNICAL FIELD OF THE INVENTION

10 This invention relates generally to a method for forming a multi-colored or
two-toned decorative outer class A surface or first surface on a skin or panel.

INVENTION BACKGROUND

15 Currently, multi-colored or two-tone decorative surfaces are produced on
skins or panels by a number of different processes. In general, these processes can
be categorized as either coating methods such as painting; or infusion methods
such as material pigmentation, i.e., mixing color into plastics materials before the
materials are formed into skins or panels.

20 Processes that employ infusion include slush mold processes where pre-
pigmented dry particulate plastic materials are cast against a heated slush mold
surface. The cast materials melt on the heated surface to form a shell or skin.
Various methods for producing multi-colored or two-tone decorative surfaces
includes the use of one or more gaskets in the slush molding process. According to
25 one method, one or more gaskets are used to form a decorative surface on a plastic
skin or panel comprising at least two distinct separate areas of plastic material. The
gasket is pressed against a heated slush mold surface to separate castings of
different-colored charges of dry, particulate plastics material.

30 Another method for producing multi-colored or two-tone decorative
surfaces on skins or panels using pre-pigmented plastic materials includes the
masking of certain areas on a heatable slush mold surface. According to this

method, a first or "outer" layer is formed by casting a first plastics material against a portion of the heated mold surface. The masking is then removed and a second or "inner" layer is formed by casting a second plastic material of a different color or shade against the outer layer and also onto the exposed areas of the heated mold surface that had been masked during the first casting step.

Each of the above slush mold methods produces a plastic skin or panel having a composite two-tone outer surface. Because the two plastic materials forming the composite surface are cast against the same heated mold surface they form respective outer surfaces that lie flush in relation to each other. In other words, the composite surface is a single-level, smooth surface.

It is also known, in certain automotive applications, for skins, such as seat upholstery, to include textured surfaces comprising a plurality of small diameter cylindrical depressions or through-holes. The depressions or holes formed in these skins are on the order of one millimeter in diameter and are closely spaced in a regular pattern across an entire outer exposed surfaces of such skins.

What is needed is a quick and accurate method for mass producing skins or panels having multi-colored or two-tone designs on an outer surface of each skin or panel.

SUMMARY OF THE INVENTION

According to the invention, a method is provided for forming a design in a panel (12). The method includes providing an outer layer (16), an inner layer (18) and providing the outer layer (16) on the inner layer (18) in a layered disposition. The method further includes providing a design (14) in the panel (12) by forming voids (17) in the outer layer (16) that expose the inner layer (18).

The voids (17) are provided in the outer layer (16) by exposing predetermined regions of the outer layer (16) to a laser beam (32) capable of

burning, evaporating or otherwise removing portions of the outer layer (16) in each exposed region. The employment of laser technology allows detailed designs to be created in the outer class A surfaces of large numbers of like panels both quickly and accurately in an assembly line process.

5

BRIEF DRAWING DESCRIPTION

To better understand and appreciate the invention, refer to the following detailed description in connection with the accompanying drawings:

10 Figure 1 is a perspective view of a plastic panel having a design formed according to the inventive method;

 Figure 2 is a partial cross-sectional edge view of the plastic skin of Figure 1 before design formation;

15 Figure 3 is a partial cross-sectional edge view of the plastic skin of Figure 1;

 Figure 4 is a schematic front view of the panel of Figure 1 supported on a holding fixture and being lased by a laser beam from a laser gun, a laser controller and a laser drive mechanism constructed according to the invention, an alternate holding fixture drive mechanism being shown in phantom;

20 Figure 5 is a partial cross-sectional edge view of the plastic skin of Figure 1 with outer and inner layers bonded together by an adhesive; and

 Figure 6 is a perspective view of a panel having a tear seam formed according to the inventive method to aid in the deployment of an air bag from behind the panel.

25

PREFERRED EMBODIMENT DESCRIPTION

 A two-tone design formed on and into an outer surface 10 of a plastic skin or panel 12 according to the inventive method is generally indicated at 14 in
30 Figures 1 and 3. According to the method, the skin or panel 12 is first manufactured without a design as shown in Figure 2. The skin or panel 12 is manufactured to include at least two layers as shown at 16 and 18 in Figures 1-3.

The two layers may completely overlap through the skin or panel, or may partially overlap in an area where the design is to be applied according to the invention. The two layers 16, 18 comprise respective first and second materials of different appearance, preferably plastic materials. The difference in appearance between the
5 respective first and second plastic materials may be due to differences in any one of a number of different visually discernable attributes including but not limited to color, intensity, texture, pattern, gloss, and thickness.

As used herein, a difference in appearance may be visually discernable
10 via ordinary viewing with the naked eye or where more objectivity is desired, discernable via a difference in numeric values as measured by any industry accepted appearance measurement test. For color, difference is preferably measured as the difference in any individual numerical reading obtained from a spectrophotometer using the CIE 1976 L* a* b* scales. For texture, which
15 includes attributes such as grain, orange peel, and surface roughness, a profilometer is preferred to obtain numerical differences. For gloss, a gloss meter is preferred to measure differences in degree of reflective light.

The skin component may be formed from one or more plastics materials
20 including but not limited to polyvinyl chlorides (PVC), thermoplastic urethanes (TPU), thermoplastic olefins (TPO), thermoset urethanes, polyesters, rubbers, polypropylenes, and polyethylenes. The layers 16, 18 may be formed by any known method including but not limited to casting, vacuum forming, blow molding, injection molding, rotational molding, and spray coating. The layers 16,
25 18 may each be formed separately and then bonded together, or may be manufactured as a single composition including two or more layers 16, 18. In the embodiment of Figures 1-3 the outer layer 16 is of a light colored plastics material and has a thickness of approximately .010", but may be as little as .001" as in the case of a spray coating. The second or underlying layer 18 shown in Figures 1-3 is
30 of a darker colored plastics material and has a thickness of approximately .040". As shown in Figures 1 and 3, the areas where portions of the first or outer layer 16 have been removed leave exposed the underlying, darker second layer 18. While

plastic materials are preferred, other materials which could be substituted in any combination and in any relative position including but not limited to textiles, leather, metals, wood, and natural and synthetic resins.

5 After formation, the skin or panel 12 is transported from a manufacturing area to a laser station shown schematically in FIG. 4. At the laser station the skin or panel 12 is placed on a holding fixture 30 and the outer surface 10 of a first 16 or "outer" one of the two layers 16, 18 is exposed to a laser beam 32 produced by a laser beam generator 34 of a laser gun 36 and delivered by a beam delivery
10 mechanism 38 of the gun 36. The laser gun 36 may be connected to an electronic controller 40 programmed to provide and remove the laser beam 32 by either energizing and deenergizing the beam generator 34 or by directing and redirecting or blocking and unblocking the laser beam 32 generated by the beam generator 34. The controller 40 may also be programmed to command a laser gun drive
15 mechanism 42 to move the laser beam 32 to various predetermined points on the panel 12 or to direct the laser beam 32 toward some point away from the panel. The electronic controller 40 may be programmed to move the laser beam 32 in accordance with a predetermined program to a predetermined series of positions adjacent portions of the outer surface 10 of the first or outer layer 16 of the skin or
20 panel 12 that are to be removed to expose corresponding portions of a second 18 or underlying one of the two layers 16, 18 in a predetermined pattern to form a desired pattern. In each position of the predetermined series of positions the controller 40 then commands the laser gun 36 to operate in such a way as to cause an emitted laser beam 32 to burn away, evaporate or otherwise remove portions of the first
25 layer 16 of the panel 12 to leave corresponding voids 17 that expose corresponding portions of the second layer 18 beneath. As shown in Figures 1 and 3, the laser beam 32 may also be caused to burn a short distance into the second layer 18 to insure that the second material is exposed despite any variations in thickness in the first layer 16.

30

As shown in phantom in FIG. 4, a holding fixture drive 44 may be operatively connected to the holding fixture 30 and/or the panel 12 in place of the

laser gun drive 42. In such embodiments the controller 40 is connected to the fixture drive 44 and programmed to move the panel 12 in accordance with a predetermined program to a predetermined series of positions holding portions of the outer surface 10 in the path of the laser beam 32 to form the desired pattern.

5

The removed portions and resulting voids 17 may be of any configuration, size and number to create a desired decorative effect. The configuration of the voids 17 may include holes of various shapes, as shown at 20 in Figures 1 and 3; lines as shown at 22, Figure 1; and/or logos, or logo enhancements as shown at 24 in Figure 1. In addition, a number of voids 17 may be arranged to form a composite logo image or other design 14. The various configurations of voids 17 could, for example, be formed on automotive seat covers or interior trim panels. In other embodiments the voids 17 may be configured to provide decoration and/or first surface weakening of a supplemental inflatable restraint (SIR) door opening.

10
15

The skin or panel described above is preferably of a type used for a vehicle trim panel. However, other uses include, but are not limited to toys, construction, furniture, luggage, or any other application where such an aesthetic appearance or function is desirable.

20

As set forth in the claims, the method includes providing an outer panel layer 16 comprising a first plastic material and an inner panel layer 18 comprising a second plastic material that is different in appearance than the first material. The difference in appearance between the first and second materials may be due to differences in any one of a number of different visually discernable attributes such as color, intensity, texture pattern, gloss, and thickness. The inner and outer panel layer 16s may be the inner and outer panels 12 of an automotive seat cover or of an interior automotive trim panel 12.

25

30

As shown in FIG. 5, in providing the outer layer 16 on the inner layer 18 in a layered disposition, an adhesive 50 may first be provided between the outer

and inner layers 18. Alternatively, the outer and inner layers 18 may be formed by casting the first and second materials, in powder or particulate form, against a heated mold surface in a slush molding process.

5 A design 14 is provided in the panel 12 by forming voids 17 in the outer layer 16 such that the inner layer 18 is exposed and visible through the voids 17. The voids 17 may be formed to create a desired decorative effect by, for example, configuring the voids 17 to include holes of various shapes such as linear shapes 22, logos or logo enhancements 24, composite logo images and/or
10 designs 14 formed by providing a number of voids 17 adjacent one another in a predetermined pattern. As shown in FIG. 6, other embodiments may include a weakened region as shown at 46 comprising a plurality of voids 17' provided in a pattern 46 or a weakened region as shown at 48 comprising a single elongated void 17'. Each of these weakened regions 46, 48 are formed in an outer layer 16'
15 of a multi-layer panel 12' and define a supplemental inflatable restraint door opening.

The voids 17 are provided by exposing predetermined regions of the outer layer 16 to a laser beam 32 capable of burning, evaporating or otherwise
20 removing portions of the outer layer 16 in each exposed region. A desired remaining thickness of the second material may be provided beneath each void by causing the laser to burn through the outer layer 16 and, controllably, a desired fixed depth into the inner layer 18.

25 The laser beam 32 is directed by connecting a controller 40 to a drive mechanism 42 that is operatively connected to either the panel 12 or a laser beam delivery mechanism 38. The controller 40 is programmed to create a predetermined design 14 by commanding the drive mechanism 42 to move one of the panel 12 and the laser beam 32 in a predetermined pattern relative to one
30 another. The controller 40 is also programmed to turn off or redirect the laser when the laser beam 32 has cut to a predetermined depth in to the panel 12.

- 8 -

I intend this description to illustrate certain embodiments of the invention rather than to limit the invention. Therefore I have used descriptive words rather than limiting words.

- 5 . Obviously, it's possible to modify this invention from what the description teaches. One may practice the invention other than as described.

What is claimed is:

1. A method for forming a design in a panel (12); the method including the steps of:

- 5 providing a panel outer layer (16);
 providing a panel inner layer (18);
 providing the outer layer (16) on the inner layer (18) in a layered disposition;
 providing a design (14) by forming voids (17) in the outer layer (16), the
10 voids (17) exposing the inner layer (18); and
 providing the voids (17) by exposing predetermined regions of the outer layer (16) to a laser beam (32) capable of burning, evaporating or otherwise removing portions of the outer layer (16) in each exposed region.

15 2. The method of claim 1 in which:

 the step of providing an outer layer (16) includes providing a layer comprising a first material; and

 the step of providing the inner layer (18) includes providing a layer that comprises a second material different in appearance from the first material.

20

 3. The method of claim 1 in which:

 the step of providing an outer layer (16) includes providing an outer skin (16) for an automotive seat cover (12); and

 the step of providing an inner layer (18) includes providing an inner layer
25 (18) of an automotive seat cover (12).

 4. The method of claim 1 in which:

 the step of providing an outer layer (16) includes providing an outer skin (16) for an automotive interior trim panel (12); and

30 the step of providing an inner layer (18) includes providing an inner layer (18) of an automotive interior trim panel (12).

- 10 -

5. The method of claim 1 including the additional step of providing an adhesive (50) between the outer and inner layers (16, 18) before the step of providing the outer layer (16) on the inner layer (18).

5 6. The method of claim 1 in which the step of providing the outer layer (16) on the inner layer (18) and the steps of providing the outer and inner layers (16, 18) include casting the first and second materials against a heated mold surface.

10 7. The method of claim 1 in which the step of providing a design (14) includes forming the voids (17) in a predetermined pattern to create a desired decorative effect.

15 8. The method of claim 1 in which the step of providing a design (14) includes configuring the voids (17) to include holes (20) of various shapes.

9. The method of claim 1 in which the step of providing a design (14) includes providing the voids (17) in a pattern forming a weakened region (46, 48) in the outer layer (16) defining a supplemental inflatable restraint door opening.

20 10. The method of claim 1 in which the step of providing the voids (17) includes providing a desired remaining thickness of the second material beneath each void (17) by causing the laser beam (32) to burn through the outer layer (16) and a desired depth into the inner layer (18).

25 11. The method of claim 1 in which the step of providing the voids (17) includes directing the laser beam (32) by connecting a controller to a drive mechanism that is operatively connected to one of the panel (12) and a laser beam delivery mechanism (38) of a laser gun (36), the controller being programmed to
30 create a predetermined design (14) by commanding the drive mechanism to move one of the panel (12) and the laser beam (32) in a predetermined pattern relative to one another.

- 11 -

12. The method of claim 11 in which the step of providing the voids (17) includes connecting a controller (40) to the laser gun (36), the controller (40) being programmed to turn off or redirect the laser beam (32) once the laser beam (32) has cut to a predetermined depth into the panel (12).

5 .









FIG-3FIG-4

FIG-5FIG-6

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/02863

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B44C1/22 B44C3/00 B60R13/02 B60N2/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B44C B60R B60N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 44 19 197 A (VOLKSWAGENWERK AG) 15 December 1994 (1994-12-15) column 1, line 58 -column 2, line 5 ---	1,2
X	PATENT ABSTRACTS OF JAPAN vol. 012, no. 485 (M-777), 19 December 1988 (1988-12-19) & JP 63 205291 A (NKK CORP), 24 August 1988 (1988-08-24) abstract ---	1,2
X	FR 2 575 114 A (CALVADOS HUBERT) 27 June 1986 (1986-06-27) page 1, line 28 -page 2, line 19 page 3, line 1 - line 12 -----	1,2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 June 2000

Date of mailing of the international search report

08. 09. 2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
Fax: (+31-70) 340-3016

Authorized officer

Herrmann, J

INTERNATIONAL SEARCH REPORT

In ternational application No.
PCT/US 00/02863

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1(partially) and 2

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

1. Claim : 1 (partially) and 2
claim 1 (partially) and and claim 2
2. Claim : 1 (partially) and 3
1 (partially) and claim 3
3. Claim : 1 (partially) and 4
1 (partially) and claim 4
4. Claim : 1 (partially) and 5
1 (partially) and claim 5
5. Claim : 1 (partially) and 6
1 (partially) and claim 6
6. Claim : 1 (partially) and 7
1 (partially) and claim 7
7. Claim : 1 (partially) and 8
1 (partially) and claim 8
8. Claim : 1 (partially) and 9
1 (partially) and claim 9
9. Claim : 10
1 (partially) and claim 10
10. Claims: 1 (partially), 11 and 12
1 (partially) and claim 11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/02863

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 4419197 A	15-12-1994	NONE	
JP 63205291 A	24-08-1988	NONE	
FR 2575114 A	27-06-1986	NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.